



#### Flatness tolerances : waviness

	H/L en %	
	Annealed	Temper rolled $\leq 1,5$ mm
Standard	$\leq 3$ %	$\leq 2$ %
Tight	$\leq 2$ %	$\leq 1$ %
Precision	$\leq 1$ %	$\leq 0,75$ %

#### Coil set tolerances

	Coil mm EN 10151
Standard	$\leq 20$ mm
Tight	$\leq 10$ mm
Precision	$\leq 6$ mm

#### Cross Bow tolerances

	$l \leq 10$	$10 < l \leq 150$	$150 < l \leq 720$
Standard	2 %	1 %	0,80 %
Precision	1 %	0,50 %	0,50 %